



CHARACTERISTICS

- Gray coloration
- 50% visible light transmittance (VLT)
- Super hydrophobic
- Self-healing
- Anti-yellowing
- Anti-contamination

APPLICATIONS

For automotive use
(other uses may apply).

APPLICATION AREAS

Vehicle headlights and taillights

APPLICATION METHOD

Light protection films are to be professionally installed by trained, authorized installers.

SHELF LIFE

Light protection films should be installed within one year from the date of purchase.

LAYER DESCRIPTIONS

CapSheet
Protects film before use

Self-Healing Top Coat
Hydrophobic and scratch-resistant

TPU
High-clarity and impact-resistant

Pressure-Sensitive Adhesive (PSA)
For easy installation

Release Liner
Protects film before use

LAYER THICKNESS

210 ± 10 μ m

STEK® Paint Protection Film Technical Data Sheet

PRODUCT IMAGE




STORAGE INSTRUCTIONS

Recommended Temperature Range: 20±2 °C (68±2 °F)
Recommended Relative Humidity: 40-60%

Avoid extreme temperature ranges in storage. Store the product in its original packaging in a horizontal orientation, away from direct sunlight. Do not place heavy objects on top of the packaging, as this may damage the product.

STRUCTURE



PROPERTIES

Gloss	>90 Gu	ASTM D523
Coating Layer Crack	>60 mm	ASTM D412
Adhesion (30 min.)	>1300	ASTM D3330
Adhesion (24 hrs)	>1500	
Self-Healing	Super	
Hydrophobicity	Super hydrophobic	
Weathering	No change 6500 W Xenon Arc Irradiance: 051 W/m ² (340 nm), 65° C Humidity: 50%, R.H. 1000 hrs	

PACKAGE DIMENSIONS

Box size
730 x 185 x 180 (mm)

Technical Data Sheet

ROLL CONFIGURATIONS

24 In. x 50 ft	(610 mm x 15m)
----------------	----------------

NOTES

All data have been collected by STEK Automotive through internal testing standards and methods. Results may differ when using other testing standards.

Reported values are expected properties and should not be used for product certification.

The provided technical information consists of representative product data and should not be used for specification purposes. Unless otherwise noted, all tests are performed at room temperature.

All concerns regarding warranty and liability are subject to the terms and conditions of sale. When applicable, these terms and conditions are governed by prevailing laws.

Prior to application, the user must determine the suitability of the product for its intended use, and assumes all risk and liability therein.